

**POLYESTER RESIN COMPOSITION****BEST AVAILABLE COPY**

**Patent number:** JP60202148  
**Publication date:** 1985-10-12  
**Inventor:** YOSHIDA TOMOHIKO; AOKI YOSHIHISA  
**Applicant:** MITSUBISHI RAYON CO  
**Classification:**  
- international: C08K3/32; C08K5/49; C08K7/14; C08K13/04;  
C08L67/02; C08L69/00  
- european:  
**Application number:** JP19840057364 19840327  
**Priority number(s):** JP19840057364 19840327

**Report a data error here****Abstract of JP60202148**

**PURPOSE:** The titled compsn. with excellent appearance giving a molded product with little shrink mark, which comprises a polyethylene terephthalate resin, glass fiber, a P compd. and a specified polycarbonate resin. **CONSTITUTION:** 30-98.985wt% polyethylene terephthalate resin prepd. by copolymerizing a linear polyethylene terephthalate homopolymer contg. an ethylene terephthalate unit as the constituent unit with a small amt. of a copolymn. component [(iso)phthalic acid], 1-60wt% chopped strand-type glass fiber 0.4-6mm. in length, 0.01-5wt% P compd. such as triphenyl phosphate and 0.005-5wt% at least one polycarbonate resin selected from among resins having at least three average repeating unit of the formula (wherein R1-8 is H or halogen; R9-10 is alkyl) are mixed in a mixer such as a tumbler followed by melt kneading.

---

Data supplied from the esp@cenet database - Worldwide